

U.S. Patent Application Serial No. 10/537,376
Amendment filed September 2, 2009
Reply to OA dated June 2, 2009

AMENDMENTS TO THE SPECIFICATION:

Amend the specification as follows:

Please replace the paragraph beginning at page 4, line 15 and ending at page 5, line 8, with the following rewritten paragraph:

That is, the present invention provides, in a first aspect, a calcium phosphate base particulate compound satisfying the following expressions (a) to (d):

(a) $20 \leq S_w \leq 300 \text{ (m}^2\text{/g)}$;

(b) $1 \leq T_g \leq 150 \text{ (mg/g)}$;

(c) $0.005 \leq D_{x50} \leq 0.5 \text{ (}\mu\text{m)}$; and

(d) $1.5 \leq D_{x50}/\sigma_x \leq 20$

wherein,

S_w : BET specific surface area ($\text{m}^2\text{/g}$) measured by nitrogen adsorption method,

T_g : heat loss (mg/g) per 1 g of calcium phosphate base particulate compound from ~~30 to 250°C~~ 250 to 500°C,

D_{x50} : cumulative 50% average diameter (μm) counted from larger particle side based on the observation by transmission electron microscope (TEM),

U.S. Patent Application Serial No. **10/537,376**
Amendment filed September 2, 2009
Reply to OA dated June 2, 2009

σ_x : standard deviation $\{\ln(D_{x16}/D_{x50})\}$; and

D_{x16}: cumulative 84% average diameter (μm) counted from larger particle side based on the observation by transmission electron microscope (TEM).

Please replace the paragraph beginning at page 48, line 18 and ending at page 49, line 1, with the following rewritten paragraph:

Using the half wavelength film, an incoming side polarization film, a first half wavelength film, a second half wavelength film, and an outgoing side polarization film were laminated using an adhesive in this order while the polarization axis of the coming-in side polarization film was set to be 0 degrees, the delay phase axis of the first half wavelength film was set to be 22.5 degrees, the delay phase axis of the second half wavelength film was set to be 67.5 degrees, and the polarization axis of the outgoing side polarization film was set to be 90 degrees. The transmission spectra of the laminated film (~~[[450 nm]]~~ 400 nm, 550 nm, and 700 nm) are shown in Table 6.